

EVERCOAT®

INNOVATIVE SOLUTIONS
THAT PERFORM.

EASY SAND™



Flowable polyester finishing and blending putty

+

The very latest filler technology

Self-levelling

Fast repair of small dents and damage

Eliminates pin-holes and heavy sand scratches

Ideal for smart and spot repair

Even, pin-hole free application of material

EASY SAND is a next generation self-levelling polyester finishing and blending putty. The product has been specially formulated to reduce the working time and speed up the repair process without any concession to quality. It contains special ingredients that reduce the heat generated by sanding, allowing a faster sanding process without clogging the paper. Due to its exceptional self-levelling properties, it is ideal for the effective repair of hail damage over large areas. The direct application over abraded OEM paint keeps the repair area relatively small. This speeds up the repair of stone-chips, dents, micro-pinholes as well as deep sand scratches. EASY SAND is therefore the ideal product for all smart and spot repair applications.

EASY SAND™
101669 – 880 ml

*Test it yourself and
experience the many
advantages it brings to
your repair process!*

TECHNICAL DATA SHEET

EVERCOAT®

EASY SAND™

Flowable polyester finishing and blending putty

Edition: SP04.00556 - Rev.01 | Page 1/2

DESCRIPTION AND APPLICATION	FOR PROFESSIONAL USE ONLY Self-levelling polyester finishing and blending putty for the filling and levelling of small areas of damage such as stone-chips, dents, scratches, sanding marks, micro-pinholes and for large areas of hail damage.																
SUBSTRATES	Exceptional adhesion to a variety of suitably abraded substrates including; OE paint & clearcoat, steel, galvanised steel, zinc coated steel, aluminium, composite plastics, hard plastics, SMC, polyester filler.																
PREPARATION	Before sanding, thoroughly clean the area to be repaired removing all traces of dirt, oil and wax residues. Lightly abrade the repair area to key the surface P80-P180. Use a fine abrasive to remove any deep or heavy scratch P180-P220. pattern. Remove the dust. The area to be repaired must be completely dry before application of product.																
MIXING	The mixing ratio is 2% by weight. Place the required amount of hardener on a clean, grease free, mixing board and add the requisite 2% hardener. Thoroughly mix the material to a consistent, homogeneous mass that is one uniform colour. Only use the EVERCOAT hardener provided.																
APPLICATION	First, apply a very thin layer of mixed material with firm pressure to the repair area. This promotes an optimum, pin-hole free application and excellent adhesion. Increase to the desired depth of repair by applying layers of product. Do not apply over freshly coated surfaces or coated surfaces that have not completely cured. Allow to dry completely before finishing.																
FINISHING	Usually the sanding process can begin after 10-15 mins. Abrade the stopper with P180 – P320 grit, avoiding deep sand scratches outside of the repair area.																
TECHNICAL DATA	<table border="1"><tr><td>Color</td><td>White</td></tr><tr><td>Physical state</td><td>Liquid</td></tr><tr><td>Solubility</td><td>Not soluble in cold and warm water</td></tr><tr><td>Working time</td><td>5-6 minutes</td></tr><tr><td>Dry to sand time</td><td>10-15 minutes</td></tr><tr><td>Maximum build</td><td>3 mm (sanded)</td></tr><tr><td>Ingredients and Precautions</td><td>Safety data sheet (MSDS) available on request</td></tr><tr><td>VOC</td><td>EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC</td></tr></table> <p>The properties are typical values and not to be considered as technical sales specifications. The physical test was at about 25 °C and 75 % relative humidity unless otherwise specified.</p>	Color	White	Physical state	Liquid	Solubility	Not soluble in cold and warm water	Working time	5-6 minutes	Dry to sand time	10-15 minutes	Maximum build	3 mm (sanded)	Ingredients and Precautions	Safety data sheet (MSDS) available on request	VOC	EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC
Color	White																
Physical state	Liquid																
Solubility	Not soluble in cold and warm water																
Working time	5-6 minutes																
Dry to sand time	10-15 minutes																
Maximum build	3 mm (sanded)																
Ingredients and Precautions	Safety data sheet (MSDS) available on request																
VOC	EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 97 g/l VOC																
STABILITY	Best before date: 18 month from manufacturing date The manufacturing date is within the batch-identification number on the bottom of the can or on the label. The batch-identification is composed as follow: 8 10 233 8 = year 2018 10 = month Octobre 233 = running batch number																
STORAGE	According to the requirements of local regulations. Observe the precautionary statements given on the label. Maximum storage temperature 25 ° C. Store in a cool, well-ventilated place away from incompatible materials and sources of ignition. Keep away from oxidising agents, strong alkalis and acids. Smoking is prohibited in the immediate vicinity. Prevent unauthorized access. Opened containers should be closed carefully and tightly. Keep upright to prevent leakage. Do not empty into drains. Do not return mixed material to the original container.																
SAFETY INSTRUCTIONS	Be sure to read all instructions and warnings before using EVERCOAT products. Safety data sheets for all materials are available online at https://itwevercoat-sds.thewerco.com/ .																

EVERCOAT



Official distributor
partner for Europe

Your EVERCOAT partner:

INDASA - INDÚSTRIA DE ABRASIVOS, S.A.

Apartado 3005
3801-101 Aveiro, Portugal
Tel. +(351) 234 303 600
Fax +(351) 234 303 605
E-mail: indasa@indasa.pt