

# Technical Data Sheet



Peter Kwasny GmbH, Heilbronner Str. 96  
74831 Gundelsheim / Germany  
Phone: +496269 95-0, Fax: +496269 95-80  
www.spraymax.com / www.kwasny.com / info@kwasny.de

## **SprayMax®** **1K UNIFILL - NEU S1 500 ml** **Art. Nr. 680420**



### **Product**

#### **Description / Purpose**

High build Primer Filler that is suitable for sanded-through areas with high layer thickness. Suitable for steel, galvanised steel, aluminium, various plastics.

#### **Properties**

- High layer thicknesses
- Fast drying
- Fast layer thickness build-up
- Corrosion protection

#### **Material base**

Acrylic resins

#### **Colour**

White

#### **Gloss level**

matt

#### **VOC Value (EU)**

676 g/l

### **Substrate**

Steel (cleaned and sanded)

Galvanised steel (hot-galvanised, strip galvanised and electro-galvanised cleaned and sanded)

Aluminium, soft aluminium (cleaned and sanded)

Various Plastics

Due to the large number of plastic types, compatibility with the substrate has to be tested before in each individual case.

Polyester surfaces (cleaned and sanded)  
 Old paint and factory paint (cleaned and sanded)  
 The damaged area must be dry and free of grease  
 and dust and all rust needs to be removed.


## **Processing**

### **Protection measures**




Wear personal protection equipment.  
 (respiratory mask/gloves/goggles)  
 For more information, see safety data sheet.

### **Shake**




Shake can thoroughly for at least 2 minutes from  
 when the mixing balls are heard.

### **Spray to test**




After shaking the can, test spray and check  
 compatibility with the surface and the colour.

### **Spraying distance**




10 cm - 15 cm

### **Spray passes**




Dry film thickness up to 150 µm  
 (approx. 2 - 3 spray coats) 35 µm per layer

### **Flash-off time**




Flash time: between 2 spray coats (until matt) / 5 min.

### **Processing conditions**



Optimum application at 18° C - 25° C and a relative  
 humidity from 40 - 60 %.

### **Drying**



TG1 dust dry: 2 - 5 min  
 TG3 dry to touch: 5 - 10 min  
 Ready for sanding: 45 min

The stated values refer to the above-mentioned  
 processing conditions. The level of dryness is  
 determined pursuant to DIN 53150.


## Continue




IR: 5 - 8 min.

Observe equipment description

Can be topcoated with all conventional 1K or 2K top coats, and solvent and water-based paints. Check compatibility with the surface.




For dry sanding with a machine, the use of soft discs with foam backing P 360 - P 500 is recommended.



Wet sanding by hand with P 500 - P 800

## Finish



After painting, turn the can upside down and spray for 3 - 5 seconds to clean the valve.

## Additional Information

### Important Information




Avoid bumps, friction and impact.

Not suitable for plastic parts made from PE, PP, PP blends like PP/EPDM and polystyrene. Use SprayMax® 1K Plastic Adhesion Promoter 680009 first.

Do not use on thermoplastic paintwork.

Do not topcoat with 2K UP putties.

### Shelf Life



60 months

The usage period refers to an unused can that is stored correctly at a temperature of 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

## Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

## Note

For professional use only.

For labelling see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved We reserve the right to update, amend or supplement the content of the information without prior notice.